



## RG Acrylic Protector for Asphalt



(60102114 / 15L)

### UPDATE

---

**April 26, 2018**

Make sure that you have an up-to-date technical data sheet in hand by consulting our Web site: [techniseal.com](http://techniseal.com)  
Canada and U.S.A.: dial 1 800 465-7325  
Others: dial (514) 523-8324 (Canada)

### APPLICATIONS

---

- Driveways, commercial parking lots, pedestrian areas, etc.

### PROPERTIES

---

- Evens and rejuvenates the look of the surface
- Does not contain bitumen
- Covers up to 60 m<sup>2</sup> (655 sq. ft.)

### DESCRIPTION

---

Made of acrylic resin, RG Acrylic Protector for Asphalt extends the life of your asphalt while improving its original look. It prevents deterioration caused by chemical products such as fertilizers, calcium, vehicles fluids, etc. Waterproof, it forms a protective coat against the elements of the harsh Canadian climate. Water based, RG Acrylic Protector for Asphalt does not release unpleasant fumes, and is environmentally friendly.

### DIRECTIONS

---

#### BEFORE YOU BEGIN

- Do not apply to asphalt previously sealed with a coal-tar-based product.
- Do not apply with a squeegee.
- Wait 3 to 6 months before applying to new asphalt.
- Apply to bare asphalt or to asphalt previously sealed with a water-based acrylic.
- Wait at least 2 years before recoating.
- ALWAYS TEST on a small hidden area of approximately 0.4 m<sup>2</sup> (4 sq. ft.) to ensure that result meets your expectations (see Warranty).

**SURFACE PREPARATION (ESSENTIAL)**

1. Cover vegetation, vehicles and adjacent surfaces that are not to be treated.
2. Wash the entire surface using a water jet, then let dry thoroughly.
3. Remove oil stains with Techniseal® Dirt and Grease Cleaner for Asphalt (142-511).
4. Apply Techniseal® Oil-Spot Primer (142-761) to previously cleaned areas.
5. Repair damaged areas (cracks, potholes and troughs) with the appropriate Techniseal® repair products.

**APPLICATION**

**Application Conditions:**

- Surface must be clean, dry and warm to the touch.
- Preferably apply early in the morning; temperature must be between 15°C and 25°C.
- No rain forecasted for the next 24 hours.
- Sprinkler system must be turned off.
- Use a consistent application method over the entire surface.

**Required Tools:**

- Techniseal® Slit-Foam Roller (145-930)
- Airless sprayer for high-viscosity paints (optional)

Do not dilute. Shake well or stir product before and during application.

Roller Application: Saturate surface with a coat of protector, avoiding accumulation of excess product. Maintain a wet edge in order to prevent overlap marks.

Sprayer Application: Work in sections of no more than 9.2 m<sup>2</sup> (100 sq. ft.). Saturate surface with a coat of protector. With the roller, remove excess before it dries. Repeat for subsequent sections, maintaining a wet edge in order to prevent overlap marks.

Second Coat (for optimal protection or to mask repairs): Once surface is dry (+/- 24 hours), apply a second coat following the same method.

Traffic: Pedestrian: 24 h. / Vehicular: 48 h. Block access during that period.

**CAUTION**

- Do not attempt sprayer application on windy days.
- Application to excessively hot asphalt will make Protector dry too quickly and will leave overlap marks.
- An over-accumulation of product could generate flaking.
- Heavy traffic could prematurely alter the look of the Protector.

**COVERAGE**

15 L covers up to 655 sq. ft. (60 m<sup>2</sup>). Quantity required will vary depending on surface condition (new asphalt is usually more porous). It is recommended that a small area be tested to determine the exact amount needed.

**STORAGE**

Keep from freezing. Store in a cool, dry place.

**CLEANING & DISPOSAL**

Wash tools and hands with warm soapy water. Consult your retailer or your appropriate community agency for disposal of empty containers or unused product.

**PACKAGING**

Name	Product code	Retail Size	Units per pallet
RG	60102114 (142-123)	15 L	60

## WARNING

---

KEEP OUT OF REACH OF CHILDREN. FIRST AID TREATMENT If swallowed, call a Poison Control Centre or doctor immediately. Do not induce vomiting. If in eyes, rinse with water for 15 minutes. If on skin, rinse well with water

Coating Category: Any flat coating (VOC Concentration Limit: 100g/L)

## SHIPPING

---

### Land

NOT REGULATED

### Sea

UN3082

Environmentally hazardous substance, liquid, n.o.s. (Dibutyl phthalate)

Class: 9

PG: III

## LIMITED WARRANTY

---

Having no control over the use of the products, Techniseal® does not guarantee finished work. Replacement of any defective product shall be the buyer's sole remedy under this warranty. A proof of purchase will be required for any claim. Before using this product, user shall determine the suitability of the product for its intended use, and user alone assumes all risks and liability whatsoever in connection therewith. User shall test product in a small inconspicuous area (approx. 0.4 m<sup>2</sup> – 4 sq. ft.) under projected conditions of use. In the event that no test was carried out, the warranty will only apply to 0.4 m<sup>2</sup> (4 sq. ft.). This limited warranty excludes any liability for any consequential, incidental, indirect or special damages. Except for the limited warranty made above, manufacturer specifically disclaims and excludes any other express warranty, any implied warranty of merchantability of goods, and implied warranty of fitness of goods for any particular purpose.